

AD-753 479

STABILIZATION OF HIGH-PRESSURE POLY-  
ETHYLENE BY NEW ANTIOXIDANTS-PRODUCTS  
OF THE CYCLOALKYLATION OF PHENOL AND o-,  
m-, AND p-CRESOLS AND 1,2-DIHYDRO-  
NAPHTHALENE

S. F. Neumova, et al

Foreign Technology Division  
Wright-Patterson Air Force Base, Ohio

15 November 1972

DISTRIBUTED BY:

**NTIS**

National Technical Information Service  
U. S. DEPARTMENT OF COMMERCE  
5285 Port Royal Road, Springfield Va. 22151

AD753479

FPD-HT-23-1096-72


## FOREIGN TECHNOLOGY DIVISION



STABILIZATION OF HIGH-PRESSURE POLYETHYLENE  
BY NEW ANTIOXIDANTS - PRODUCTS OF THE  
CYCLOALKYLATION OF PHENOL AND o-, m-, AND  
p-CRESOLS AND 1,2-DIHYDRONAPHTHALENE

by

S. F. Naumova, M. V. Balykina,  
and Ye. N. Artsimenya



Approved for public release;  
distribution unlimited.

Reproduced by  
NATIONAL TECHNICAL  
INFORMATION SERVICE  
U S Department of Commerce  
Springfield VA 22151

19

UNCLASSIFIED  
Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Foreign Technology Division Air Force Systems Command U. S. Air Force		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
		2b. GROUP	
3. REPORT TITLE STABILIZATION OF HIGH-PRESSURE POLYETHYLENE BY NEW ANTIOXIDANTS - PRODUCTS OF THE CYCLOALKYLATION OF PHENOL AND o-, m-, AND p-CRESOLS AND 1,2-DIHYDRONAPHTHALENE			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Translation			
5. AUTHOR(S) (First name, middle initial, last name)  Naumova, S.F.; Balykina, M.V.; Artsimenya, Ye.N.			
6. REPORT DATE 1971		7a. TOTAL NO. OF PAGES 89	7b. NO. OF REFS 9
8a. CONTRACT OR GRANT NO.		8b. ORIGINATOR'S REPORT NUMBER(S) FTD-HT-23-1096-72	
b. PROJECT NO. 7343			
c.		8b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.			
10. DISTRIBUTION STATEMENT  Approved for public release; distribution unlimited.			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Foreign Technology Division Wright-Patterson AFB, Ohio	
13. ABSTRACT  The product of cycloalkylation of phenol, o cresol, m cresol, and p cresol by 1,2 dihydronaphthalene were recommended as antioxidants for stabilizing high pressure poly ethylene. AP1152729			

DD FORM 1473  
1 NOV 68

I a

UNCLASSIFIED

Security Classification

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Polyethylene Phenol Cresol Naphthalene Alkylation Chemical Stabilizer Antioxidant Additive						

If

UNCLASSIFIED

Security Classification

FTD-HT- 23-1096-72

## EDITED TRANSLATION

FTD-HT-23-1096-72

STABILIZATION OF HIGH-PRESSURE POLYETHYLENE  
BY NEW ANTIOXIDANTS - PRODUCTS OF THE  
CYCLOALKYLATION OF PHENOL AND o-, m-, AND  
p-CRESOLS AND 1,2-DIHYDRONAPHTHALENE

By: S. F. Naumova, M. V. Balykina,  
and Ye. N. Artsimenya

English pages: 5

Source: AN BSSR. Doklady, Vol. 15, No. 4,  
1971, pp 325-327.

Requester: ASD

Translated by: Charles T. Ostertag Jr.

Approved for public release;  
distribution unlimited.

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION DIVISION  
FOREIGN TECHNOLOGY DIVISION  
WP-AFB, OHIO.

FTD-HT- . 23-1096-72

Date 15 Nov 19 72

IC

# U. S. BOARD ON GEOGRAPHIC NAMES TRANSLITERATION SYSTEM

Block	Italic	Transliteration	Block	Italic	Transliteration
А а	<i>А а</i>	A, a	Р р	<i>Р р</i>	R, r
Б б	<i>Б б</i>	B, b	С с	<i>С с</i>	S, s
В в	<i>В в</i>	V, v	Т т	<i>Т т</i>	T, t
Г г	<i>Г г</i>	G, g	У у	<i>У у</i>	U, u
Д д	<i>Д д</i>	D, d	Ф ф	<i>Ф ф</i>	F, f
Е е	<i>Е е</i>	Ye, ye; E, e*	Х х	<i>Х х</i>	Kh, kh
Ж ж	<i>Ж ж</i>	Zh, zh	Ц ц	<i>Ц ц</i>	Ts, ts
З з	<i>З з</i>	Z, z	Ч ч	<i>Ч ч</i>	Ch, ch
И и	<i>И и</i>	I, i	Ш ш	<i>Ш ш</i>	Sh, sh
Й й	<i>Й й</i>	Y, y	Щ щ	<i>Щ щ</i>	Shch, shch
К к	<i>К к</i>	K, k	Ъ ъ	<i>Ъ ъ</i>	"
Л л	<i>Л л</i>	L, l	Ы ы	<i>Ы ы</i>	Y, y
М м	<i>М м</i>	M, m	Ь ь	<i>Ь ь</i>	'
Н н	<i>Н н</i>	N, n	Э э	<i>Э э</i>	E, e
О о	<i>О о</i>	O, o	Ю ю	<i>Ю ю</i>	Yu, yu
П п	<i>П п</i>	P, p	Я я	<i>Я я</i>	Ya, ya

\* ye initially, after vowels, and after ъ, ь; e elsewh-re.  
 When written as ѐ in Russian, transliterate as yě or ü.  
 The use of diacritical marks is preferred, but such marks  
 may be omitted when expediency dictates.

STABILIZATION OF HIGH-PRESSURE  
POLYETHYLENE BY NEW ANTIOXIDANTS -  
PRODUCTS OF THE CYCLOALKYLATION  
OF PHENOL AND o-, m-, AND p-CRESOLS  
AND 1,2-DIHYDRONAPHTHALENE

S. F. Naumova, M. V. Balykina,  
and Ye. N. Artsimenya

(Presented by Academician B. V.  
Yerofeyev, AN BSSR).

Recently particular attention has been gained by the problem of stabilization of polyethylene during the aging process. For the stabilization of dark parts made from polyethylene compounds from the class of amines are recommended in the literature [1-5], and also a mixture of sulfurous compounds with carbon black. For the stabilization of light parts it is recommended to use dicresyl propane [6] and a number of compounds of the type 2,2'-alkylene-bis-(4,6-dialkylphenol) [7, 8]. In work [9] a study is made of the stabilizing action of alkyl- and arylalkylphenols. It is shown that replacement of the alkyl substituent by a phenylethyl in the ortho-position in phenols increases their stabilizing action during the aging of polyethylene. A proposal has been expressed concerning the influence of the phenols of the intermolecular hydrogen bond of the OH-group with substituents on the stabilizing action.

Physico-mechanical properties of 10802-020 high-pressure polyethylene stabilized by antioxidants - products of cycloalkylation of phenol and o-, m-, and p-cresols by 1,2-dihydronaphthalene in the process of rolling at a temperature of 160°C.

Composition	Concentration of antioxidant	Time of rolling	Indices of quality					
			tensile strength, kgf/cm <sup>2</sup>	yield stress, kgf/cm <sup>2</sup>	relative elongation, %	kg·10 <sup>-4</sup>	melting index g/10 min;	amount of gel fraction, %
Non-stabilized polyethylene 10802-020;	0	10 min 8 hr	120 102	100 96	543 217	1,60 41,9	2,0 did not flow	— —
Polyethylene 10802-020 + + antioxidant - product of cycloalkylation of phenol by 1,2-dihydronaphthalene with MV 225;	1	10 min 8 hr	117 123	97 7	603 616	4,0 3,7	2,29 1,16	0 0
Polyethylene 10802-020 + + antioxidant - product of cycloalkylation of phenol by 1,2-dihydronaphthalene with MV 301;	0,5	10 min 8 hr	122 125	117 124	540 542	— —	— —	— —
	1,0	10 min 12 hr	130 128	116 119	570 549	7,9 6,8	— —	0 1,6
Polyethylene 10802-020 + + antioxidant - product of cycloalkylation of o-cresol by 1,2-dihydronaphthalene with MV 217 ± 12;	0,5	10 min 8 hr	119 122	108 113	571 565	7,9 6,8	— —	0 1,6
	1,0	10 min 8 hr	119 134	108 120	581 577	4,7 3,9	— —	0 0
		12 hr	116	116	494	—	—	0
Polyethylene 10802-020 + + antioxidant - product of cycloalkylation of m-cresol by 1,2-dihydronaphthalene with MV 301;	0,5	10 min 8 hr	134 129	119 116	567 530	2,8 5,2	2,0 1,6	0 0
Polyethylene 10802-020 + + antioxidant - product of cycloalkylation of p-cresol by 1,2-dihydronaphthalene with MV 345 ± 15.	1,0	10 min 8 hr	125 128	103 119	480 576	4,3 3,8	— —	0 0



It is interesting to explain the effect of the stabilizing action by aryl-substitutes of phenol and cresols on polyethylene in the case of thermooxidative aging.

In this connection we synthesized new antioxidants - aryl phenol and aryl cresols - by means of the reaction of cycloalkylation of phenol and isomeric cresols by 1,2-dihydronaphthalene.

It is necessary to note that neither the synthesis of antioxidants on the basis of products of cycloalkylation of phenol and cresols by dialin nor the investigation of their stabilizing action have been described in the literature up to now. The effectiveness of the stabilizing action of aryl phenols and aryl cresols on the basis of 1,2-dihydronaphthalene (dialin) was determined by comparing the rate of aging of high-pressure polyethylene in the presence of stabilizers with the rate of aging of non-stabilized polyethylene. Brand 10802-020 polyethylene was subjected to accelerated aging by means of rolling on roll mills at 160°C. The rate of aging of polyethylene samples was evaluated based on the changes in physico-mechanical indices during the process of rolling, including relative elongation during fracture, dielectric loss tangent, etc. The results obtained are summed up in the table, from which it is apparent that all the first products of cycloalkylation of phenol and cresols by 1,2-dihydronaphthalene which were synthesized by us are effective stabilizers. The properties of polyethylene after 8-12 hours of accelerated thermal aging on roll mills remain practically constant and are not changed, while for polyethylene without the antioxidant added in 8 hours the dielectric loss tangent increases by 26 times and relative elongation is reduced by 2.5 times (in respect to the initial sample of polyethylene).

It is necessary to note the preference of products of cycloalkylation of p-, m-, and o-cresols by dialin. These products,

thanks to the presence of a substitute for the  $-CH_3$  group in the benzene ring of phenol, combine better with polyethylene.

Light stabilized compositions of polyethylene were obtained on the basis of polyethylene and products of the cycloalkylation of phenol and cresols by 1,2-dihydronaphthalene. An investigation of the IR-spectra of absorption of the products of cycloalkylation of phenol and cresols by dialin showed that they all have ortho-substitution in the benzene ring of phenol in respect to the OH-group. Thus it was proven that usually phenols which are dissolved in carbon tetrachloride have one band of absorption in the range of  $3600-3610\text{ cm}^{-1}$  corresponding to valence variation of non-associated OH-group. In the aryl phenols and aryl cresols which we synthesized with a dialin substitute in the ortho-position along with the band of absorption in the range of  $3620\text{ cm}^{-1}$  a second band appears in the area of  $3540-3580\text{ cm}^{-1}$ . This can be related to the OH-group in the ortho-position, bound by a hydrogen bond with  $\pi$ -electrons of the benzene ring. Apparently the high effectiveness of the stabilizing action of the products of cycloalkylation of phenol and cresols by 1,2-dihydronaphthalene is conditioned by ortho-substitution to the -OH-group of phenol and cresols by dialin and the hydrogen bond between the -OH group and the benzene ring. Such a position was noted earlier in work [9] for alkyl-, alkylaryl-substituted phenols.

Thus for the first time in the literature we synthesized new effective antioxidants - stabilizers on the basis of products from the cycloalkylation of phenol and cresols by 1,2-dihydronaphthalene and investigated their stabilizing action on high-pressure polyethylene.

Polotskiy Chemical Combine  
imeni 50th Anniversary of the BSSR,  
Institute of Physical and Organic  
Chemistry, AN, BSSR.

Received  
8 October 1970

FTD-HT-23-1096-72

## BIBLIOGRAPHY

<sup>1</sup> Патенты США № 2651620, 2651626. <sup>2</sup> Канадский патент № 498915. <sup>3</sup> C. J. Meyers. Ind. Eng. Chem., 44, 5, 1095, 1952. <sup>4</sup> High Polymers Ind. Eng. Chem., 11, Pittsburg, 1952. <sup>5</sup> Chem. Eng. News, 35, 37, 66, 1957. <sup>6</sup> Materie Plastice, 19, 5, 361, 1953. <sup>7</sup> Canad Plast, April, 48, 1956. <sup>8</sup> Патент США № 2830034. <sup>9</sup> И. П. Лазарева, И. А. Обольянина, Г. С. Попова, Пластмассы, № 4, 44, 1963.